



GRISWOLD LLC
PO Box 638, One River Street
Moosup, Connecticut 06354-0638
Tel: 800.472.8788 / 860.564.3321
Fax: 860.564.9103
www.griswoldllc.com

KUSHON[®] Sponge
3120SP
And polyester fabric
1/8" and greater
Typical Physical Properties

PROPERTY	TEST METHOD	VALUE
PHYSICAL		
Density (Average), lb./ft ³	ASTM D1056	30
Thickness, inches (Tolerance)	ASTM D1056	To 0.187 (± 0.015) 0.188 - 0.374 (± 0.030) 0.375 - 0.500 (± 0.040) Over 0.500 (± 0.060)
Standard Color		Black
Polymer		Natural Rubber
Compression Force Deflection, psi	ASTM D1056 at 25% compression	9 - 17
Accelerated Aging, %	ASTM D573 Change in compression deflection 168 hr at 158°F	± 20
Temperature Range		-20°F to 160°F
Fabric		100% Polyester Circular Knit

NOTE: Information of a technical nature is based on laboratory tests which either GRISWOLD LLC conducts or sends to an independent laboratory for testing for determination of uses as requested in writing by customer. GRISWOLD LLC believes these to be reliable. However, GRISWOLD LLC has no control over the application of the material to, or part of, the final **product** and **therefore**, GRISWOLD LLC makes **no express or implied warranty of result, fitness or merchantability**. The customer should determine reliability for the end use or particular application.

10/01/2015 JJT