



GRISWOLD LLC
 PO Box 638, One River Street
 Moosup, Connecticut 06354-0638
 Tel: 800.472.8788 / 860.564.3321
 Fax: 860.564.9103
 www.griswoldllc.com

KUSHON[®] Sponge
4134
 Typical Physical Properties

PROPERTY	TEST METHOD	VALUE
PHYSICAL		
Density, lb./ft ³	ASTM D1056	27
Thickness, inches		See table
Dimensional Specification, inches		See table
Standard Color		Tan
Polymer		Natural Rubber
Compression Force Deflection, psi	ASTM D1056 at 25% compression	8 - 12
Compression Set, % max.	ASTM D1056 50% deflection for 22 hr at 158°F	15
Recovery, % min.	50% deflection for 22 hr at 70°F	95
Accelerated Aging, %	ASTM D1056 Change in compression deflection 168 hr at 158°F	± 20
Linear Shrinkage, % max.	168 hr at 158°F	2

Drum Gasket Dimensional Specifications

Thickness	Width	Minimum Thickness	Maximum Thickness	Minimum Width	Maximum Width	Minimum Length	Maximum Length
5/16	5/16	0.281	0.344	0.281	0.344	-0.5	+0.5
3/8	3/8	0.313	0.438	0.313	0.438	-0.5	+0.5
3/8	1/2	0.313	0.438	0.438	0.562	-0.5	+0.5
7/16	7/16	0.375	0.500	0.375	0.500	-0.5	+0.5
1/2	1/2	0.450	0.550	0.450	0.550	-0.5	+0.5

NOTE: Information of a technical nature is based on laboratory tests which either GRISWOLD LLC conducts or sends to an independent laboratory for testing for determination of uses as requested in writing by customer. GRISWOLD LLC believes these to be reliable. However, GRISWOLD LLC has no control over the application of the material to, or part of, the final **product** and **therefore**, GRISWOLD LLC makes **no express or implied warranty of result, fitness or merchantability**. The customer should determine reliability for the end use or particular application.

10/01/2015 JJT