



GRISWOLD LLC
PO Box 638, One River Street
Moosup, Connecticut 06354-0638
Tel: 800.472.8788 / 860.564.3321
Fax: 860.564.9103
www.griswoldllc.com

KUSHON[®] Sponge

Jar Opener* 9233

Typical Physical Properties

PROPERTY	TEST METHOD	VALUE
PHYSICAL		
Density, (Average), lb./ft ³	ASTM D1056	41
Thickness, inches (Tolerance)	ASTM D1056	.050 (.045 - .065)
Standard Color		Orange
Polymer		Natural Rubber/SBR
Compression Force Deflection, psi	ASTM D1056 at 25% compression	22+
Compression Set, % max.	ASTM D395 50% deflection at 158°F (70°C)	70
Accelerated Aging, %	ASTM D573 Change in compression deflection 168 hr at 158°F (70°C)	+25

*Custom colors available

NOTE: Information of a technical nature is based on laboratory tests which either GRISWOLD LLC conducts or sends to an independent laboratory for testing for determination of uses as requested in writing by customer. GRISWOLD LLC believes these to be reliable. However, GRISWOLD LLC has no control over the application of the material to, or part of, the final **product** and **therefore**, GRISWOLD LLC makes **no express or implied warranty of result, fitness or merchantability**. The customer should determine reliability for the end use or particular application.

03/30/2016 JJT