



GRISWOLD LLC
PO Box 638, One River Street
Moosup, Connecticut 06354-0638
Tel: 800.472.8788 / 860.564.3321
Fax: 860.564.9103
www.griswoldllc.com

KUSHON[®] Sponge
ZX892
And polyester fabric
1/8" and greater
Typical Physical Properties

| PROPERTY | TEST METHOD | VALUE |
|--|--|--|
| PHYSICAL | | |
| Density (Average), lb./ft ³ | ASTM D1056 | 30 |
| Thickness, inches (Tolerance) | ASTM D1056 | To 0.187 (± 0.015) 0.188 - 0.374 (± 0.030) 0.375 - 0.500 (± 0.040) Over 0.500 (± 0.060) |
| Standard Color | | Black |
| Polymer | | Natural Rubber |
| Compression Force Deflection, psi | ASTM D1056 at 25% compression | 9 - 18 |
| Accelerated Aging, % | ASTM D573 Change in compression deflection 168 hr at 158°F | ± 20 |
| Temperature Range | | -20°F to 160°F |
| Fabric | | 100% Polyester Circular Knit |

NOTE: Information of a technical nature is based on laboratory tests which either GRISWOLD LLC conducts or sends to an independent laboratory for testing for determination of uses as requested in writing by customer. GRISWOLD LLC believes these to be reliable. However, GRISWOLD LLC has no control over the application of the material to, or part of, the final **product** and **therefore**, GRISWOLD LLC makes **no express or implied warranty of result, fitness or merchantability**. The customer should determine reliability for the end use or particular application.

10/01/2015 JJT