



GRISWOLD LLC
 PO Box 638, One River Street
 Moosup, Connecticut 06354-0638
 Tel: 800.472.8788 / 860.564.3321
 Fax: 860.564.9103
 www.griswoldllc.com

enlighten- microcellular polyurethane

U5B32

Preliminary Typical Physical Properties

PROPERTY	TEST METHOD	VALUE
PHYSICAL		
Density, lb./ft ³ (kg/m ³) Tolerance, %	ASTM D3574 (1,4)	33 (529) ± 10
Thickness, inches (mm) Tolerance, mils	(4,5)	0.036 (0.91) - 0.096 (2.41) -5 / +20
Standard Color (Pantone® code)		Dark Gray (0424)
Compression Force Deflection, psi (kPa) Typical psi (kPa)	ASTM D3489 (1,4) at 25% compression	38 - 54 (268 - 372) 46 (317)
Compression Set, % max. (Typical)	ASTM D3574-D (1,3) at 50% compression, 73°F (23°C)	5 (0.5)
Tensile Strength, min. psi (kPa) Typical psi (kPa)	ASTM D3574-E Die A (4)	180 (1241) 265 (1827)
Tensile Elongation, % min. Typical	ASTM D3574-E Die A (2)	100 167
Foam/Substrate Peel, g/in	20 IPM @ 180°	TBD
Resilience (Ball Rebound), %	ASTM D3574-H	16 ± 2

- (1) Sample size is 1.5 inch diameter by approximately 0.5 inch stack height
- (2) Based on Grip separation
- (3) Ct method, percent of original thickness
- (4) All metric conversions are approximate
- (5) ASTM D3574 method with the following exceptions: 1.5 inch diameter foot on digital thickness indicator with a force loading of 0.9 Newtons (91.8 grams-force) plus the 30 gram weight of the foot

NOTE: Information of a technical nature is based on laboratory tests which either GRISWOLD LLC conducts or sends to an independent laboratory for testing for determination of uses as requested in writing by customer. GRISWOLD LLC believes these to be reliable. However, GRISWOLD LLC has no control over the application of the material to, or part of, the final **product** and **therefore**, GRISWOLD LLC makes **no express or implied warranty of result, fitness or merchantability**. The customer should determine reliability for the end use or particular application.