



GRISWOLD LLC
 PO Box 638, One River Street
 Moosup, Connecticut 06354-0638
 Tel: 800.472.8788 / 860.564.3321
 Fax: 860.564.9103
 www.griswoldllc.com

enlighten- microcellular polyurethane

U7Y17

Typical Physical Properties

PROPERTY	TEST METHOD	VALUE
PHYSICAL		
Density, lb./ft ³ (kg/m ³) Tolerance, %	ASTM D3574 (1,6)	18.0 (289) ± 10
Thickness, inches (mm) Tolerance, %	(6,8)	0.093 - 0.500 (2.4 - 12.5) ± 10
Standard Color (Pantone® code)		Black (0426)
Compression Force Deflection, psi (kPa) Typical psi (kPa)	ASTM D3489 (1,6) at 25% compression	7 - 14 (48 - 96) 10.8 (74)
Compression Set, % max. (Typical)	ASTM D3574-D (1,3) at 50% compression, 73°F (23°C)	2 (1.7)
	ASTM D3574-D (1,3) at 50% compression, 158°F (70°C)	10 (2.9)
	ASTM D3574-J2 & -D (1,3,4) Autoclave then 50% compression, 158°F (70°C)	5 (2.4)
Tensile Strength, min. psi (kPa) Typical psi (kPa)	ASTM D3574-E Die A (6)	100 (689) 183 (1261)
Tensile Elongation, % min. Typical	ASTM D3574-E Die A (2)	100 167
Tear Strength, min. pli (kN/m) Typical pli (kN/m)	ASTM D624 Die C (6)	12 (2.1) 22 (3.8)
Resilience (Ball Rebound), %	(7)	14
TEMPERATURE RESISTANCE		
Continuous Use Range	SAE-J-2236	-40° to 225°F (107°C)
Intermittent Use Maximum		250°F (121°C)

- (1) Sample size is 1.5 inch diameter by approximately 0.5 inch stack height
- (2) Based on grip separation
- (3) Ct calculation, percent of original thickness
- (4) Autoclaved for 5 hours at 250°F then test D
- (5) Based on internal testing, samples to be submitted for official certification
- (6) All metric conversions are approximate
- (7) Result in units from dropping a 5/8 inch diameter steel ball, weighing approx. 16.7 grams onto foam stacked to a height of one inch, from a height of 100 units where each unit is equivalent to 0.2 inches and recording the height the ball rebounds to
- (8) ASTM D3574 method with the following exceptions: 1.5 inch diameter foot on digital thickness indicator with a force loading of 0.9 Newtons (91.8 grams-force) plus the 30 gram weight of the foot

NOTE: Information of a technical nature is based on laboratory tests which either GRISWOLD LLC conducts or sends to an independent laboratory for testing for determination of uses as requested in writing by customer. GRISWOLD LLC believes these to be reliable. However, GRISWOLD LLC has no control over the application of the material to, or part of, the final product and therefore, GRISWOLD LLC makes **no express or implied warranty of result, fitness or merchantability.** The customer should determine reliability for the end use or particular application.