

Customer:	General Motors
Specification No:	GMW 14196 (May 2016)
Product Description & Uses:	High density, cellular, polyurethane with low compression set For gaskets in vibration damping, vibration and shock isolation


GM Grade: Type 3/Type 4

Product: U7E21XXX0426

Property	Test Method	Units	Specification	Result
Mass	GMW 3182	g/m ²	Per Engineering Drawing	1002
Thickness	ISO 2589	mm	Per Engineering Drawing	3.21
Odor	GMW 3205	rating	6 min.	8.5 wet, 10 dry
Flammability (as rec'd) (machine direction)	FMVSS 302	mm/min	102 max.	19, 35, 18, 34, 31
	GMW 3232	mm/min	100 max.	Bstat – 53 (conforming) Bmax – 35 (conforming)
Flammability (as rec'd) (cross-machine direction)	FMVSS 302	mm/min	102 max.	35, 14, 34, 36, 11
	GMW 3232	mm/min	100 max.	Bstat – 64 (conforming) Bmax – 36 (conforming)
Flammability (cycle aged) (machine direction)	FMVSS 302	mm/min	102 max.	29, 30, 31, 26, 28
	GMW 3232	mm/min	100 max.	Bstat – 35 (conforming) Bmax – 31 (conforming)
Flammability (cycle aged) (cross-machine direction)	FMVSS 302	mm/min	102 max.	28, 20, 16, 31, 29
	GMW 3232	mm/min	100 max.	Bstat – 45 (conforming) Bmax – 31 (conforming)
Fogging	GMW 3235	visual inspect	No oily film, droplets or crystals and ≤2 mg condensate	0.3 Dry uniform fog conforming
Compression Set - 50%	ISO 1856 Method A	%	10% max.	0.8
CFD at 40% Compression	ISO 3386-1	kPa	50 – 99 Type 3 100 – 175 Type 4	117
Emission Report	GMW 15634			Attached

Results compiled from testing performed by Intertek, Report No. 102970798GRR-001 Dated May 4, 2017

GRISWOLD LLC



John J. Tichy, Jr.
Technical Director

NOTE: Information of a technical nature is based on laboratory tests which either GRISWOLD LLC conducts or sends to an independent laboratory for testing for determination of uses as requested in writing by customer. GRISWOLD LLC believes these to be reliable. However, GRISWOLD LLC has no control over the application of the material to, or part of, the final **product** and **therefore**, GRISWOLD LLC makes **no express or implied warranty of result, fitness or merchantability**. The customer should determine reliability for the end use or particular application.

Test Report for:

Griswold LLC

GMW15634 (November 2014)

GMW15635 (August 2012)

Emissions Testing:

VOC/SVOC Analysis

Carbonyl Analysis

Materials:

Microcellular Polyurethane Foam Rolls

Part Numbers:

U7E211250426201


U7E171250426204

U7H200930427201

U7H151250427204

U7S151250426201

U7Y201250426201



KYLE TANIS
Project Engineer



TAYLOR GEBBEN
Reviewer

DESCRIPTION OF SAMPLES:

Product Name	Microcellular Polyurethane Foam
Product Category	Automotive Interior
Product Numbers	U7E211250426201 U7E171250426204 U7H200930427201 U7H151250427204 U7S151250426201 U7Y201250426201
Date of Manufacture	Not Specified
Date of Shipment	03/09/17
Date Received by Lab	03/13/17
Dates Tested	03/15/17 - 03/18/17
As Received Sample Condition	Good condition
Sample Condition	Production
Material Specification	GMW14196 (2016)
Lab Sample ID	GRR1703131303-006
Samples Submitted	(6x) Polyurethane foam rolls

WORK REQUESTED / APPLICABLE DOCUMENTS:

VOC/SVOC Analysis:	GMW15634 (November 2014)
Carbonyl Analysis:	GMW15635 (August 2012)

CONCLUSIONS:

VOC/SVOC Analysis:	Results Reported
Carbonyl Analysis:	Conforming

This report shall not be reproduced except in full without the written approval of the testing laboratory.

VOC / SVOC ANALYSIS

Description of Samples:

Product Name	Microcellular Polyurethane Foam
Product Category	Automotive Interior
Product Number	U7E211250426201, U7E171250426204, U7H200930427201, U7H151250427204, U7S151250426201, U7Y201250426201
Date of Manufacture	Not Specified
Date of Shipment	03/09/17
Date Received by Lab	03/13/17
As Received Sample Condition	Good condition
Sample Condition	Production
Material Specification	GMW14196 (2016)

Test Conditions:

Dates Test Performed	03/15/17 – 03/18/17
Test Method	GMW15634 (November 2014)
Sample Conditioning	24 hour preconditioning followed by 16+ hours uncovered at 23°C / 50%RH
Sample Size	15 ± 2 mg
Desorption Temperature	VOC – 90°C and SVOC – 120°C
Desorption Time	VOC – 30 minutes and SVOC – 60 minutes
Constant Flow Rate	42 mL/min
Number of Samples	Two (2) samples per material; twelve (12) total
Acceptance Criteria	Referencing GMW16853 (July 2013), Table 4, F7: Results Reported Referencing GMW3059 Appendix C (October 2015), Supplement CG4110 (October 2015) Individual VOC - See Appendix B of this report

Facilities and Equipment:

Instrumentation Used:	Markes TD-100 Thermal Desorption Agilent 7890A GC Agilent 5975C MS
Column Used:	Agilent HP-Ultra 2 (GC)

This report shall not be reproduced except in full without the written approval of the testing laboratory.

Test Summary:

The emissions testing were performed according to GMW15634, "Determination of Volatile and Semi-Volatile Organic Compounds from Vehicle Interior Materials". After conditioning, samples were prepared to the specifications outlined by Appendix C in the test method and placed in a glass thermal desorption tube. Samples were then subjected to thermal desorption as outlined in the test method and VOC/SVOC emissions were trapped on a sorbent cold trap held at -30°C. These emissions were separated and characterized using gas chromatography with mass selective detection. Total and individual emissions were calculated as equivalent to toluene and n-hexadecane standard calibrations that were run concurrently with the samples. Substance determinations are made using a library match of >90% to the mass fragmentation pattern observed. The prefixed "?" with substance names is included following Appendix E, Table E1 of GMW15634 since a confirmation by retention time was not obtained as these compounds were not included in the calibration mix defined in GMW15634. All single substances measuring in excess of 1.0 ppm (based on calibration compound equivalency) were identified.

This report shall not be reproduced except in full without the written approval of the testing laboratory.

VOC / SVOC ANALYSIS

Client / Sample Information			
Test Lab:	Intertek - GRR	Technician:	Kyle Tanis
Client Name:	Griswold LLC	Signature:	<i>Kyle Tanis</i>
Sample ID:	U7E211250426201	Date of Analysis:	03/20/17
Date of Manufacture:	Not Specified		
Date of Sampling:	Not Specified		
Overall Weight in Vehicle (g):	Not Specified		
Overall Dimensions of Part (mm):	Not Specified		
	<i>Sample 1</i>	<i>Sample 2</i>	
Dimensions (mm):	5.1 x 3.1 x 2.5	5.2 x 3.1 x 2.7	
Mass (g):	0.01475	0.01503	

Total VOC / SVOC Emissions Results				
	Limits (µg/g)	Calculated Results (µg/g)		Disposition
VOC	Report Values	Sample 1:	235.3	N/A
		Sample 2:	220.1	N/A
SVOC	Report Values	Sample 2:	285.5	N/A

This report shall not be reproduced except in full without the written approval of the testing laboratory.

Individual VOC Emissions Results (as toluene equivalent)				
Retention Time (min)	Substance Name (with Observed Mass Fragmentation)	CAS No.	Substance Area	Concentration (ppm)
9.659	? Acetylacetone 100 85 72 43 41	123-54-6	233531	22.24
19.516	? Unknown compound 102 87 57 43 39	-	162889	15.51
26.376	? 2-Oxepanone 114 84 70 55 42	502-44-3	576851	54.94
26.649	? Unknown compound 128 110 83 69 55	-	51221	4.88
30.348	? Unknown compound 135 107 83 68 55	-	463767	44.17
33.622	? Unknown compound 142 124 84 70 55	-	65642	6.25
34.363	Tetradecane 99 85 71 57 43	629-59-4	10761	1.02
34.583	? Unknown siloxane 255 281 221 147 73	-	14405	1.37
34.959	? Unknown compound 157 129 117 115 103	-	35298	3.36
36.413	? Unknown compound 415 327 281 147 73	-	19483	1.86
36.549	? Unknown compound 113 98 67 55 41	-	13234	1.26
36.866	? Butylated Hydroxytoluene 220 205 189 145 115	128-37-0	100664	9.59
37.691	? Unknown siloxane 355 295 221 147 73	-	49958	4.76
38.286	? Diphenyl sulfide 186 185 171 152 109 77	139-66-2	182296	17.36

Individual VOC Emissions Results (as toluene equivalent) - CONTINUED				
Retention Time (min)	Substance Name (with Observed Mass Fragmentation)	CAS No.	Substance Area	Concentration (ppm)
38.877	? Decanedioic acid, dimethyl ester 199 166 157 74 55	106-79-6	51112	4.87
39.140	? Unknown siloxane 401 355 281 147 73	-	19773	1.88
39.960	? Unknown compound 295 281 221 147 73	-	59240	5.64
40.677	? Unknown compound 115 97 69 55 41	-	74015	7.05
41.185	? Unknown siloxane 429 255 281 221 73	-	14366	1.37
41.809	? Unknown siloxane 295 281 221 147 73	-	32909	3.13
42.941	? benzaldehyde, 4-(ethylphenylamino)- 225 210 196 167 77	-	49917	4.75
46.191	? Tert-octyldiphenylamine 210 194 180 167 92	-	11066	1.05

The most abundant mass fragmentation is identified by a bolded value.

This report shall not be reproduced except in full without the written approval of the testing laboratory.

Individual SVOC Emissions Results (as n-hexadecane equivalent)				
Retention Time (min)	Substance Name (with Observed Mass Fragmentation)	CAS No.	Substance Area	Concentration (ppm)
11.191	? Unknown Aromatic 157 142 117 115 91	-	55935	2.54
13.055	? Diphenyl sulfide 186 185 171 152 51	139-66-2	199466	9.05
13.231	? Decanedioic acid, dimethyl ester 199 166 125 98 55	106-79-6	268187	12.17
14.753	? Unknown ester 128 115 97 69 55	-	387314	17.57
14.978	? Unknown compound 219 184 152 108 51	-	36700	1.67
15.392	? Benzo[h]quinoline 179 151 126 98 89	230-27-3	33061	1.50
16.154	? Unknown compound 94 79 67 55 41	-	23552	1.07
16.329	? Benzenepropanoic acid, 3,5-bis(1,1-dimethylethyl)-4-hydroxy-, methyl ester 292 277 219 203 147 + ? Unknown Compound 127 111 93 81 55	6386-38-5	311421	14.13
16.505	? Dibutyl phthalate 223 205 149 121 104	84-74-2	39098	1.77
16.641	? Unknown aromatic 225 210 195 182 167	-	774186	35.13
16.705	? Unknown aromatic 225 210 195 182 167	-	36539	1.66
16.915	? Unknown silyl compound 369 355 295 221 147	-	22524	1.02
17.481	? Unknown compound 281 266 250 236 220	-	38729	1.76
18.125	? 7-Oxabicyclo[4.1.0]heptane-3-carboxylic acid, 7-oxabicyclo[4.1.0]hept-3-ylmethyl ester 143 127 110 81 41	2386-87-0	970257	44.03
18.257	? Unknown compound 295 281 266 194 73	-	79389	3.60
18.344	? Unknown compound 143 127 110 81 41	-	438631	19.90
19.720	? Tert-octyldiphenylamine 281 224 210 194 182	-	558654	25.35

This report shall not be reproduced except in full without the written approval of the testing laboratory.

Individual SVOC Emissions Results (as n-hexadecane equivalent) - CONTINUED				
Retention Time (min)	Substance Name (with Observed Mass Fragmentation)	CAS No.	Substance Area	Concentration (ppm)
19.837	? 4,4'-Di-tert-butyl-diphenylamine 281 266 250 236 220	4627-22-9	270323	12.27
20.281	? Unknown compound 156 140 124 98 58	-	39136	1.78
20.369	? Unknown compound 337 322 , 250 207 153	-	28898	1.31
21.838	? Unknown compound 390 375 219 57 43	-	93992	4.26
22.248	? Unknown compound 154 138 72 56 43	-	582059	26.41
22.394	? Unknown compound 390 375 219 57 43	-	103455	4.69
22.589	? Unknown compound 390 375 219 57 43	-	215958	9.80
22.736	? Unknown compound 390 375 219 57 43	-	45140	2.05
24.058	? Unknown compound 337 266 250 236 57	-	194264	8.81

The most abundant mass fragmentation is identified by a bolded value.

This report shall not be reproduced except in full without the written approval of the testing laboratory.

CARBONYL ANALYSIS

Description of Samples:

Product Name	Microcellular Polyurethane Foam
Product Category	Automotive Interior
Product Number	U7E211250426201, U7E171250426204, U7H200930427201, U7H151250427204, U7S151250426201, U7Y201250426201
Date of Manufacture	Not Specified
Date of Shipment	03/09/17
Date Received by Lab	03/13/17
As Received Sample Condition	Good condition
Sample Condition	Production
Material Specification	GMW14196 (2016)

Test Conditions:

Dates Test Performed	03/15/17
Test Method	GMW15635 (August 2012)
Sample Conditioning	24 hour preconditioning at 23°C / 50%RH
Sample Size	100mm x 40mm x part thickness
Bottle Size	1 Liter
Exposure Temperature	60°C ± 3°C
Exposure Duration	180 ± 15 minutes
Rest Duration	60 ± 10 minutes
Number of Samples	Two (2) samples per material; twelve (12) total
Acceptance Criteria	Referencing GMW16853 (July 2013), Table 4, F7: Formaldehyde ≤ 8 µg/g Acetaldehyde ≤ 8 µg/g Acrolein ≤ 8 µg/g Acetone: Report Value Sum of C2 to C6 Carbonyls ≤ 20 µg/g

Facilities and Equipment:

Instrumentation Used:	Agilent 1260 Infinity Series
Column Used:	Poroshell 120 EC-C18, 3x100 mm, 2.7 µm

This report shall not be reproduced except in full without the written approval of the testing laboratory.

Test Summary:

The emissions testing were performed according to GMW15635, "Determination of Aldehyde and Ketone Emissions from Interior Materials". The samples were prepared to the specifications outlined by Section 3.3.3 in the test method and suspended from a hook in a 1 liter polyethylene bottle. 50 mL of HPLC grade water was then measured into the bottles. The samples were then placed in an environmental chamber held at 60°C for a period of 180 minutes. A blank bottle was run concurrently with no sample. After the exposure and a 1 hour rest period, the sample water was combined in equal amounts with a 2,4-di-nitrophenylhydrazine (DNPH) derivatization solution and 100 µL of phosphoric acid. These samples were then analyzed using high performance liquid chromatography and aldehyde / ketone emissions were determined using calibration curves prepared from pure standards. The moisture content of the samples was determined separately according to Section 4.1.1 of the test method.

Determination of Carbonyl Compounds from Vehicle Interior Materials - GMW15635				
Client Name:	Griswold LLC	Technician:	Kyle Tanis	
Project Number:	G102970798	Date(s) Tested:	3/15/2017	
Samples Tested:	U7E211250426201	Technician Signoff:	<i>Kyle Tanis</i>	
Laboratory:	Intertek - GRR			
Sample Name:	U7E211250426201			
Part No.:	416083102			
Supplier:	N/A			
Chromatogram No.:	N/A			
Data Path:	Available upon request			
Manager:	Jesse Ondersma			
Date of Analysis:	3/16/2017			
Method:	PMD V12B_5			
Sample/Order No. (Internal)	N/A			
Date of Production:	N/A			
Date of Sample Received:	3/13/2017			
Weight of the Component in the Vehicle:	N/A			
Overall Dimensions of Component:	N/A			
		Sample 1	Sample 2	
Weight of Sample Analyzed (g):		3.94979	3.9251	
Dimensions of Sample Analyzed (mm):		99.4x40.9x3.2	99.1x40.1x3.2	
Water Content (%):		0.38	0.38	
Substance	CAS No.	Sample 1	Sample 2	Ave.
Formaldehyde	500-00-0	0.65	0.73	0.69
Acetaldehyde	75-07-0	0.22	0.12	0.17
Acetone	67-64-1	0.05	0.08	0.07
Acrolein	107-02-8	BDL	BDL	-
Propionaldehyde	123-38-6	BDL	BDL	-
Crotonaldehyde	123-73-9	BDL	BDL	-
2-Butanone	78-93-3	0.08	0.07	0.08
Methacrolein	78-85-3	BDL	BDL	-
n-Butyraldehyde	123-72-8	BDL	BDL	-
Benzaldehyde	100-52-7	BDL	BDL	-
Valeraldehyde	110-62-3	BDL	BDL	-
m-Tolualdehyde	620-23-5	0.25	BDL	0.25
Hexaldehyde	66-25-1	BDL	BDL	-
Total Carbonyls		1.26	1.00	1.13
Sum of C2to C6 Carbonyls		0.60	0.27	0.44
Comments or Specific Remarks:				
BDL* - Below Detection Limits				
The results are conforming to the acceptance criteria outlined in GMW16853.				
HPLC Instrument Model	Agilent 1260 Infinity Series			
Column Used:	Poroshell 120 EC-C18			

This report shall not be reproduced except in full without the written approval of the testing laboratory.