

Preliminary Typical Data

Product Test	Units	7110	7120	7130	7140	7150
Shore OO		34	35	36	38	40
Color		Ash				
Polymer System		Natural Rubber				
Density	Pounds / Cubic Foot	22	26	30	33	34
Compression Deflection	PSI at 25% Compression	2-5	5-10	10-16	16-22	22+
Tensile Strength	PSI	50	72	96	135	160
Tensile Elongation	%	350	245	215	140	130
Compression Set at 70 C ASTM D1056	%	15%	15%	15%	15%	40%
Temperature Range						
Upper Temp SAE J2236	Degrees C	160				
Accelerated Aging –						
% Change in Compression Deflection (168 hrs at 70 C – ASTM D1056)	% Change	20%				

